

**Test Report** 

號碼(No.): ETR24A05690 日期(Date): 06-Nov-2024 頁數(Page): 1 of 6

明輝化工實業有限公司 (MIN HUEY CHEMICALS INDUSTRIES CO., LTD.)

新北市土城區大安路138巷32號 (NO. 32, LN 138, DA'AN RD., TUCHENG DIST., NEW TAIPEI CITY 23673, TAIWAN)

以下測試樣品係由申請廠商所提供及確認 (The following sample(s) was/were submitted and identified by the applicant as):

送樣廠商(Sample Submitted By) : 明輝化工實業有限公司 (MIN HUEY CHEMICALS INDUSTRIES CO., LTD.)

樣品名稱(Sample Name) : MIN HUEY SCREEN INK (明輝油墨)

樣品型號(Style/Item No.) : 黃色系列 (無鹵) (YELLOW (NON-HALOGEN))

收件日(Sample Receiving Date) : 30-Oct-2024

測試期間(Testing Period) : 30-Oct-2024 to 06-Nov-2024

**測試需求(Test Requested) :** 依據客戶指定,測試 PAHs。 (As specified by client, to test PAHs.)

測試結果(Test Results) : 請參閱下一頁 (Please refer to following pages.)

結 論(Conclusion) : 根據客戶所提供的樣品,多環芳香烴測試結果符合德國產品安全委員會(AfPS) GS

PAHs第 3 類「其它產品」之限值要求。(Based upon the performed tests on the submitted sample(s), the test results of PAHs (15 items) comply with the limits of PAHs requirement (Category 3)「Other consumer products」 as set by

German Committee on Product Safety (AfPS) GS PAHs.)

Troy Chang / Department Manager
Signed for and on behalf of SGS TAIWAN LTD.
Chemical Laboratory - Taipei



PIN CODE: E8D4618



# **Test Report**

號碼(No.): ETR24A05690 日期(Date): 06-Nov-2024

頁數(Page): 2 of 6

明輝化工實業有限公司 (MIN HUEY CHEMICALS INDUSTRIES CO., LTD.)

新北市土城區大安路138巷32號 (NO. 32, LN 138, DA'AN RD., TUCHENG DIST., NEW TAIPEI CITY 23673, TAIWAN)

#### 測試部位敘述 (Test Part Description)

No.1 : 黃色油墨 (YELLOW INK)

#### 測試結果 (Test Results)

測試項目	測試方法	單位	MDL	結果	限值
(Test Items)	(Method)	(Unit)		(Result)	(Limit)
				No.1	
多環芳香烴 (Polycyclic Aromatic					
Hydrocarbons) (PAHs)					
苯駢(a)芘 (Benzo[a]pyrene) (CAS No.:		mg/kg	0.2	n.d.	Δ
50-32-8)					
苯駢(e)芘 (Benzo[e]pyrene) (CAS No.:		mg/kg	0.2	n.d.	Δ
192-97-2)					
苯駢蒽 (Benzo[a]anthracene) (CAS No.:		mg/kg	0.2	n.d.	Δ
56-55-3)					
苯(b)苯駢芴 (Benzo[b]fluoranthene)		mg/kg	0.2	n.d.	Δ
(CAS No.: 205-99-2)					
苯(j)苯駢芴 (Benzo[j]fluoranthene) (CAS		mg/kg	0.2	n.d.	Δ
No.: 205-82-3)					
苯(k)苯駢芴 (Benzo[k]fluoranthene)		mg/kg	0.2	n.d.	Δ
(CAS No.: 207-08-9)	参考AfPS GS 2019:01 PAK,以氣相層析儀				
菌 (Chrysene) (CAS No.: 218-01-9)	/質譜儀分析。(With reference to AfPS GS	mg/kg	0.2	n.d.	Δ
二苯駢蒽 (Dibenzo[a,h]anthracene)	2019:01 PAK, analysis was performed by	mg/kg	0.2	n.d.	Δ
(CAS No.: 53-70-3)	GC/MS.)				
苯駢菲 (Benzo[g,h,i]perylene) (CAS No.:		mg/kg	0.2	n.d.	Δ
191-24-2)					
茚酮芘 (Indeno[1,2,3-c,d]pyrene) (CAS		mg/kg	0.2	n.d.	Δ
No.: 193-39-5)					
蒽 (Anthracene) (CAS No.: 120-12-7)		mg/kg	0.2	n.d.	Δ
苯駢芴 (Fluoranthene) (CAS No.: 206-		mg/kg	0.2	n.d.	Δ
44-0)					
菲 (Phenanthrene) (CAS No.: 85-01-8)		mg/kg	0.2	n.d.	Δ
芘 (Pyrene) (CAS No.: 129-00-0)		mg/kg	0.2	n.d.	Δ
萘 (Naphthalene) (CAS No.: 91-20-3)		mg/kg	0.2	0.528	Δ
多環芳香烴15項總和 (Sum of 15 PAHs)		mg/kg	-	0.528	Δ



# **Test Report**

號碼(No.): ETR24A05690 日期(Date): 06-Nov-2024

頁數(Page): 3 of 6

明輝化工實業有限公司 (MIN HUEY CHEMICALS INDUSTRIES CO., LTD.)

新北市土城區大安路138巷32號 (NO. 32, LN 138, DA'AN RD., TUCHENG DIST., NEW TAIPEI CITY 23673, TAIWAN)

測試項目	測試方法	單位	MDL	結果	限值
(Test Items)	(Method)	(Unit)		(Result)	(Limit)
				No.1	
苊烯 (Acenaphthylene) (CAS No.: 208-	參考AfPS GS 2019:01 PAK,以氣相層析儀	mg/kg	0.2	n.d.	-
96-8)	/質譜儀分析。(With reference to AfPS GS				
苊 (Acenaphthene) (CAS No.: 83-32-9)	2019:01 PAK, analysis was performed by	mg/kg	0.2	n.d.	-
芴 (Fluorene) (CAS No.: 86-73-7)	GC/MS.)	mg/kg	0.2	n.d.	-

#### 備註(Note):

- 1. mg/kg = ppm; 0.1wt% = 0.1% = 1000ppm
- 2. MDL = Method Detection Limit (方法偵測極限值)
- 3. n.d. = Not Detected (未檢出); 小於MDL / Less than MDL
- 4. "-" = Not Regulated (無規格值)
- 5. 除非另有說明,參照ILAC-G8:09/2019決定規則,採用簡單允收規則之二分法(w=0)進行符合性判定;根據此規則,符合性結果之判定係以測試結果與限值做比較。(Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (w=0) stated in ILAC-G8:09/2019. According to this rule, the judgement of conformity is based on the comparing test results with limits.)



# **Test Report**

號碼(No.): ETR24A05690 日期(Date): 06-Nov-2024

頁數(Page): 4 of 6

明輝化工實業有限公司 (MIN HUEY CHEMICALS INDUSTRIES CO., LTD.) 新北市土城區大安路138巷32號 (NO. 32, LN 138, DA'AN RD., TUCHENG DIST., NEW TAIPEI CITY 23673, TAIWAN)

#### Remark:

# △ 德國產品安全委員會(AfPS): GS PAHs 要求 AfPS (German commission for Product Safety): GS PAHs requirements

	第1類(Category 1)	第 2 類(Category 2)		第 3 類(Category 3)		
項目 (Parameter)	意圖放入口中的材料或者長時間接觸皮膚(超過 30 秒)的 2009/48/EC 定義的玩具材料和 3 歲以下兒童使用的產品(Materials intended to be placed in the mouth, or materials in toys (Directive 2009/48/EC) or articles for children up to 3 years of age with intended	不屬於第 1 類的材料·並意圖或可預 見與皮膚接觸逾 30 秒(長期皮膚接觸) 或重複的短時間接觸(Materials that are not in Category 1, with intended or foreseeable long-term skin contact (> 30 seconds) or short-term repetitive contact with the skin)		不屬於第 1 類或第 2 類的材料·並意 圖或可預見與皮膚接觸不超過 30 秒 (短期皮膚接觸)(Materials not covered by Category 1 or 2, with		
	long-term skin contact (> 30 seconds))	供 14 歲以下兒童使	其它產品(Other consumer	供 14 歲以下兒童使 用的產品(Use by children under 14)	其它產品(Other consumer	
Naphthalene	< 1	< 2		< 10		
Phenanthrene						
Anthracene	1 Cum	e F Cum	< 10 Sum	< 20 Sum	∠ FO Cum	
Fluoranthene	< 1 Sum	< 5 Sum	< 10 Sum	< 20 Sum	< 50 Sum	
Pyrene						
Benzo[a]anthracene	< 0.2	< 0.2	< 0.5	< 0.5	< 1	
Chrysene	< 0.2	< 0.2	< 0.5	< 0.5	< 1	
Benzo[b]fluoranthene	< 0.2	< 0.2	< 0.5	< 0.5	< 1	
Benzo[j]fluoranthene	< 0.2	< 0.2	< 0.5	< 0.5	< 1	
Benzo[k]fluoranthene	< 0.2	< 0.2	< 0.5	< 0.5	< 1	
Benzo[a]pyrene	< 0.2	< 0.2	< 0.5	< 0.5	< 1	
Benzo[e]pyrene	< 0.2	< 0.2	< 0.5	< 0.5	< 1	
Indeno[1,2,3-c,d] pyrene	< 0.2	< 0.2	< 0.5	< 0.5	< 1	
Dibenzo[a,h]anthracene	< 0.2	< 0.2	< 0.5	< 0.5	< 1	
Benzo[g,h,i]perylene	< 0.2	< 0.2	< 0.5	< 0.5	< 1	
15 項 PAH 總濃度 (Sum of 15 PAH)	< 1	< 5	< 10	< 20	< 50	

單位(Unit): mg/kg



# **Test Report**


號碼(No.): ETR24A05690 日期(D

日期(Date): 06-Nov-2024

頁數(Page): 5 of 6

明輝化工實業有限公司 (MIN HUEY CHEMICALS INDUSTRIES CO., LTD.) 新北市土城區大安路138巷32號 (NO. 32, LN 138, DA'AN RD., TUCHENG DIST., NEW TAIPEI CITY 23673, TAIWAN)

#### 多環芳香烴分析流程圖 / PAHs (Poly Aromatic Hydrocarbons) analytical flow chart





# **Test Report**

號碼(No.): ETR24A05690 日期(Date

日期(Date): 06-Nov-2024

頁數(Page): 6 of 6

明輝化工實業有限公司 (MIN HUEY CHEMICALS INDUSTRIES CO., LTD.) 新北市土城區大安路138巷32號 (NO. 32, LN 138, DA'AN RD., TUCHENG DIST., NEW TAIPEI CITY 23673, TAIWAN)

\* 照片中如有箭頭標示,則表示為實際檢測之樣品/部位. \* (The tested sample / part is marked by an arrow if it's shown on the photo.)

#### ETR24A05690



\*\* 報告結尾 (End of Report) \*\*